

DATASHEET

ConcriX[®] HS 35



Product description

ConcriX HS 35 is a bi-component Macrofiber serving as a structural concrete reinforcement. The rough fiber surface ensures superior bonding within the concrete, and the fiber bundles guarantee fast three-dimensional distribution throughout the matrix during the mixing process. The enhanced technical parameters of the concrete can be used for structural design purposes.

ConcriX HS 35 serves as a structural reinforcement, increases the impact resistance of the concrete, and can also be used in structural applications.

ConcriX HS 35 prevents sedimentation – the subsequent settlement of the matrix.

ConcriX HS 35 creates a high level of resistance for concrete structures exposed to aggressive water conditions.

Application

ConcriX HS 35 is used in prefabrication applications, slabs and concrete walls, industrial floors, outside standings, for concrete repair works, concrete piles, special foundation works and different special applications.

On the basis of Eurocode 2 and the Fibre Concrete Guidelines it is possible to prove the adequate structural strength of slabs, concrete fields, foundations, walls and other structures and eliminate the steel reinforcement partially or completely.

Dosage

The recommended approximate dosage for ConcriX HS 35 as a structural reinforcement is 2.0 to 7.5 kg/m³ of concrete.

ConcriX HS 35 is available in the standard length of 35 mm.

Physical properties

Specification	Bi-component Macrofiber
Material	Polyolefine
Form	structured fibers in bundles
Bulk density	0,91
Length	35 mm, tolerance +/- 5%
Number of fibers per kilo	≈ 150'000
Color	yellow
Resistance to acids/alkalis	inert
Tensile strength	≈ 600 N/mm ²
Modulus of elasticity	> 11 GPa
Softening point	≈ 150° C
Diameter	500 µm

Processing

The original mixing times of the individual concrete formulations for most products can be retained. Special mixtures for specific products may require an extension of the mixing time.

Concrix HS 35 can be easily processed with commonly used additives.

Caution: The addition of Concrix HS 35 will increase the rigidity of the concrete!

To optimize the desired placement consistency, use concrete plasticizer!
Do not add any additional water!

Before discharging fresh concrete on site, let the drum rotate again at maximum revolution for about 2 minutes.

Packaging

Boxes	8 bags of 3 kg = 24 kg
Pallets	25 boxes / pal. = 600 kg
Big Bags and other packaging	upon request

Warranty

Concrix HS 35 fulfills the standard EN 14889-2 according to system 1 and therefore guarantees a consistently high quality.

Brugg Contec AG does not have any control over production processes using Concrix HS 35. Therefore, Brugg Contec AG declines any liability for the associated end products.

Partner for India

Grenix Projects Infra Pvt. Ltd.
#101, Plot No.52, St.No.2
Chikoti Gardens, Begumpet
Hyderabad, Andhra Pradesh - 500 016
Tel. +91-98668-02666
+91 40 2776 4900
Fax +91 40 6632 4900
vikram@grenix.in

Brugg Contec AG
Gübsenstrasse 80
CH-9015 St. Gallen
Tel. +41 71 466 12 12
Fax +41 71 466 12 10
info@bruggcontec.com
www.bruggcontec.com